

455 Gloss Aliphatic Polyurethane Topcoat

Product Data/Application Instructions

- Gloss topcoat
- Outstanding weather resistance with excellent color and gloss retention
- VOC compliant
- Resistant to broad range of corrosive atmospheres
- Resists soil pickup – cleans easily
- Cures through wide temperature range
- Hard, flexible and abrasion resistant

Typical Uses

Khemix 455 can be used as a finish coat where attractive appearance and a wide range of corrosive resistance are required.

- Chemical plants
- Pulp and paper mills
- Off shore platforms
- Petroleum refineries and containers.

Typical Properties

Chemical resistance guide

When applied over suitable primer or intermediate coat:

<i>Environment</i>	<i>Splash and Spillage</i>	<i>Fumes and Weather</i>
Acidic	VG	E
Alkaline	VG	E
Solvents	G	E
Salt solutions		
Acidic	E	E
Neutral	E	E
Alkaline	E	E
Water	E	E

G-Good

VG-Very Good

E-Excellent

*This table is only a guide. For specific recommendations, contact your **Khemix** representative for your particular corrosion protection needs. **Khemix 455** is not recommended for immersion service.*

Physical Data

Finish	Gloss
Color*	See color card
Components	2
Mixing ratio (by volume)	4 parts resin to 1 part cure

455 Gloss Aliphatic Polyurethane Topcoat

Curing mechanism	Solvent release and chemical reaction between components	
Volume Solids	66% ± 3%	
VOC (EPA Method 24)	lb/gal	g/L
unthinned	2.4	288
thinned (10% by volume)	2.8	340
Dry film thickness (per coat)	2-3 mils (50-75 microns)	
Coats	1 or 2	
Theoretical coverage		
	ft ² /gal	m ² /L
1 mil	1059	26
2 mils	530	13
Temperature resistance	°F/°C	
	wet	dry
continuous	NR	200/93
intermittent	NR	250/121
Flash Point	°F	°C
cure	92	33
resin	97	36
mixed	98	37
Thinners	Khemix 065	
Cleaner	Khemix 012	

**Certain colors (especially yellow, red and orange) may require additional coats to achieve adequate hiding, particularly when applied over dark or contrasting primer color. Color variance with rapid response tinted colors may be greater than with standard production batches. If color is critical, change batches at natural breaks in structure or intermix batches for consistency. Yellow, red and orange colors will fade faster than other colors due to the replacement of lead-based pigments with lead-free pigments in these colors.*

Typical Systems

1st Coat	2nd Coat	3rd Coat
Khemix 493	Khemix 485	Khemix 455

Surface Preparation

Coating performance, in general, is proportional to the degree of surface preparation. Refer to application instructions for specific primers and intermediate coats being used for application and curing procedures. All previous coats must be clean and dry. Adhere to all minimum and maximum topcoat times for specific primers and intermediate coats. Aged epoxy coatings must be roughened before applying **Khemix 455**.

455 Gloss Aliphatic Polyurethane Topcoat

Application Data

Substrates	Prepared and primed steel, concrete, aluminum, galvanizing, or aged coatings.			
Surface preparation:	Refer to Product Data Sheet/ Application Instructions of specific primer or intermediate coat being used.			
Steel				
Concrete				
Aluminum				
Galvanizing				
Aged coatings				
Method	Airless or conventional spray, roller, brush (touch-up only)			
Mixing ratio (by volume)	4 parts resin to 1 part cure			
Environmental conditions	°F	°C		
air and surface temp	20 to 120	-7 to 49		
Pot life (hours)		F°/C°		
	90/32	70/21	50/10	
Khemix 455	2	4	6	
Dry times		F°/C°		
	90/32	70/21	50/10	32/0
touch (minutes)	10	30	90	NR
through (hours)	4	8	24	NR
Recoat times		F°/C°		
	90/32	70/21	50/10	32/0
minimum (hours)	2	4	12	NR
maximum (days)	7	30	60	NR
Thinner	Khemix 065			
Equipment cleaner	Khemix 012			

Application Equipment

The following is a guide; suitable equipment from other manufacturers may be used. Changes in pressure and tip size may be needed for proper spray characteristics.

Airless spray—Standard equipment such as Graco, DeVilbiss, Binks, Speeflo, or others having a 28:1 or higher pump ratio and a fluid tip with 0.013- to 0.015-inch (0.33- to 0.38-mm) orifice.

455 Gloss Aliphatic Polyurethane Topcoat

Conventional spray—Industrial equipment such as DeVilbiss MBC or Binks BBR spray gun. Separate air and fluid pressure regulators, mechanical pot agitator and a moisture and oil trap in main air supply line are recommended.

Brush or roller - Natural bristle brush or solvent-resistant roller with 1/4-inch to 3/8-inch nap. For best appearance when rolling, level any air bubbles with bristle brush.

Application Procedure

Khemix 455 is packaged in two components in the proper proportions which must be mixed together before use:

1. Flush equipment with thinner or **Khemix 012** before use.
2. Stir each component thoroughly, then add cure to resin and mix until uniformly blended to a workable consistency. Do not mix more material than will be used within 4 hours at 65-80°F (18-27°C).
3. Thin only if necessary for workability.
4. When applying by conventional spray, use adequate air pressure and volume to ensure proper atomization.
5. Apply a wet coat in even parallel passes, overlap 50 percent to avoid holidays, bare areas and pinholes. If required, cross spray at right angles.
6. Application of 3 mils (75 microns) wet film thickness will normally provide 2 mils (50 microns) dry film.
7. Clean all equipment with thinner or **Khemix 012** immediately after use.
8. Keep containers tightly closed since repeated exposure to moisture will cause gelation. Moisture contaminated material is also subject to gassing on storage. Handle bulged containers with caution; lids may eject forcibly.

Shipping Data

Packaging units	1 gal	5-gal
cure	0.2 gal in 1-qt can	1 gal in 1-gal can
resin	0.8 gal in 1-gal can	4 gal in 5-gal can
Shipping weight (approx)	lb	kg
1-gal unit		
cure	2	0.9
resin	10.2	4.6
5-gal unit		
cure	9	4.1
resin	49	22

Shelf life when stored indoors at 40 to 100°F (4 to 38°C)
resin and cure 1 year from shipment date

455 Gloss Aliphatic Polyurethane Topcoat

Safety Precautions

Read each component's material safety data sheet before use. Mixed material has hazards of each component. Safety precautions must be strictly followed during storage, handling and use.

CAUTION – Improper use and handling of this product can be hazardous to health and cause fire or explosion. Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: implementation of proper ventilation, use of proper lamps, wearing of proper protective clothing and masks, tenting and proper separation of application areas. Consult your supervisor. Proper ventilation and protective measures must be provided during application and drying to keep spray mists and vapor concentrations within safe limits and to protect against toxic hazards. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interiors and buildings. This product is to be used by those knowledgeable about proper application methods. **Alspect makes no recommendation about the types of safety measures that may need to be adopted because these depend on application environment and space, of which **Alspect** is unaware and over which it has no control. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product.**

Note: Consult Code of Federal Regulations Title 29, Labor, parts 1910 and 1915 concerning occupational safety and health standards and regulations, as well as any other applicable federal, state and local regulations on safe practices in coating operations.

This product is for industrial use only. Not for residential use.

Limitation of Liability

Alspect's liability on any claim of any kind, including claims based upon **Alspect's** negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall **Alspect** be liable for consequential or incidental damages.

Warranty

Alspect warrants its products to be free from defects in material and workmanship. **Alspect's** sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at **Alspect's** option, to either replacement of products not conforming to this Warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to **Alspect** in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify **Alspect** of such nonconformance as required herein shall bar Buyer from recovery under this Warranty.

Alspect makes no other warranties concerning the product. No other warranties, whether express, implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall **Alspect** be liable for consequential or incidental damages.

455 Gloss Aliphatic Polyurethane Topcoat

Any recommendation or suggestion relating to the use of the products made by **Alspec**, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know how in the industry, and therefore it is for Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.